



## Quality Control Standard

Item	Requirement
Areas Weight(g/m <sup>2</sup> )	145 ± 3g/m <sup>2</sup>
Mesh Size(mm)	5mm × 5mm
Mark Lines	With / Without 3 Black Lines
Width(cm)	100cm
Color	White
Weight of the Raw Mesh(g/m <sup>2</sup> )	124.7g/m <sup>2</sup>
Yarn Type(tex)	Warp yarns:134tex;weft roving:375tex
Breaking strength(n/50mm)	Warp ≥ 1200N;weft ≥ 1450N
Alkali-resistance retention rate(%)	average ≥ 50% samples are soaked in 5% naoh liquid at 80°C for 6 hours
Glue Content(%)	Average glue content:14 ± 0.5%
Moisture content	≤ 0.6%
Fixation (N)	≥ 3 ± 0.5N
Roll length(m/roll)	50 ± 0.3m/roll(average value 50m/roll)
Declaration: We hereby declare that we will provide you products be in conformity with the above Quality Control Standards.	