



## Quality Control Standard

Item	Requirement
Areas Weight(g/m <sup>2</sup> )	45 ± 3g/m <sup>2</sup>
Mesh Size(mm)	2.5mm × 2.5 mm
Mark Lines	No 3 Black Lines
Width(cm)	100cm
Color	White
Weight of the Raw Mesh(g/m <sup>2</sup> )	39.0 g/m <sup>2</sup>
Yarn Type(tex)	Warp yarns:33 tex;weft roving: 33 tex
Breaking strength(n/mtr)	Warp ≥ 600N;weft ≥ 420N
Alkali-resistance retention rate(%)	average ≥ 50% samples are soaked in 5% naoh liqyid at 80°C for 6 hours
Glue Content(%)	Average glue content:16 ± 0.5%
Moisture content	≤ 0.6%
Fixation (N)	≥ 1.5 ± 0.5N
Roll length(m/roll)	50 ± 0.3m/roll (average value 50m/roll)
<b>Declaration:</b> We hereby declare that we will provide you products be in conformity with the above Quality Control Standards.	